

KEMCO GUM Jointing compound



Application area

- For connection and construction joints (up to 20 mm) on wood, plastic, mineral substrates or glass indoors and outdoors

Features

- UV- and weather-resistant
- Ready for use
- Strong adhesive
- Elastic
- Suitable to receive a further coat of KEMPEROL
- Suitable to receive paint and coloured surfacing coats
- Resin base: Polyurethane resin

Pack sizes

310 ml cartridges

12 cartridges / carton

Storage

Avoid direct sunlight and frost!

See label for use before date.

Store in closed original containers in dry rooms at temperatures between +5°C and +25°C.

Allow the material to stabilize to between +18°C and +20°C for at least 24 hours prior to use.

See label for use before date.

Consumption

min. 310 ml / 3 rm (joint width 1x1 cm)

Properties

Colour	Grey
Cured after *	approx. 1 d

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Application

Substrates must be dry, firm and free from contaminants which may affect adhesion and must be prepared accordingly.

Material, ambient air and substrate temperature must be at least +5°C to max. +30°C with a relative humidity < 80%. When executed, the surface temperature must be 3 K above the dew point.

For porous substrates, such as concrete, screed, aerated concrete blocks, wood-based materials, etc., before processing the KEMCO GUM Jointing compound with KEMCO 1K Primer, KEMCO POX 2K Primer or KEMPERTEC EP5 primer they should be primed.

Remove the aluminum cover. Pierce the protective membrane in the upper threaded part over its entire surface. Now unscrew the plastic nozzle and cut off diagonally, depending on the desired application thickness. Use the cartridge in the hand gun and in the compressed air gun (2-4 bar). Before starting the work, it is essential to check the joints to be filled, for their suitability and eliminate any possible causes of deficiencies. Trapped moisture can cause blistering and detaching. KEMCO GUM Jointing compound may only have a 2-flank adhesion during processing. Avoid a three-point adhesion by filling the joint with backfill material (z.B. PE round rubber cord).

Personal protective equipment must be worn.

GISCODE

PU40

Disposal

Liquid	EAK 08 05 01
cured	EAK 17 02 03

General information

The times given above are reduced with higher and increased with lower ambient and substrate temperatures. KEMPER SYSTEM products must not be mixed with other manufacturers' products.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is therefore essential that you always have the latest data sheet to hand. The latest version can be downloaded from kemperol.de under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application technology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery.

Issued: Vellmar, 2024-03-04