

KEMPEROL 2K-PUR Speedshot



Uses

To accelerate the reaction of KEMPEROL 2K-PUR waterproofing

Characteristics

Shortens the setting process of KEMPEROL 2K-PUR waterproofing

Pack sizes

0,9 kg in a plastic bottle with a measuring chamber

Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

Usage guide

The data refer to a quantity of 1 kg KEMPEROL 2K-**PUR** waterproofing

Tempera- ture*** [°C]		10 ml	20 ml	30 ml
5°C	V*	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V*	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h

Tempera- ture*** [°C]		10 ml	20 ml	30 ml
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

Working time

The data refer to a quantity of 2.5 kg KEMPEROL 2K-PUR waterproofing

Tempera- ture [°C]		1 Shot	2 Shot	3 Shot
		(25 ml)	(50 ml)	(75 ml)
5°C	V [*]	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V [*]	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

Working time

The data refer to a quantity of 12.5 kg KEMPEROL 2K-PUR Sealing

Tempera-		1 Shot	2 Shot	3 Shot
ture*** [°C]		(25 ml)	(50 ml)	(75 ml)
5°C	V*	-	-	22 min
	W**	-	-	4.5 h
10°C	V*	-	-	22 min
	W**	-	-	4.5 h
20°C	V*	20 min	18 min	-
	W**	7 h	6 h	-

Properties

Liquid
•

Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Further coating after

Temperature of KEMPEROL 2K-PUR Sealing

Further coating after

Temperature of KEMPEROL 2K-PUR waterproofing

Working time Further coating after Temperature of KEMPEROL 2K-PUR waterproofing



Application

Preparation

To add the correct dosage of KEMPEROL 2K-PUR Speedshot first screw the blue cap to the measuring chamber of the bottle. Then squeeze the bottle repeatedly until the dosage chamber has filled up to the 25ml line. 25 ml is one shot.

If the ambient temperature is 10°C or lower, it is recommended that you store and mix the components at room temperature.

Sachet

KEMPEROL 2K-PUR waterproofing mix in the kneading bag according to instructions, and then transfer. KEMPEROL 2K-PUR Speedshot mix with stirring rod or slow-running stirrer, streak-free into the finished waterproofing KEMPEROL 2K-PUR. Mixing time approx. 1 minute.

PPE

Personal protective equipment should be worn. We recommend a hand protection and skin protection plan adapted to the workplace. Clean the tools immediately after use with KEMCO MEK Cleaning Agent.

Important notes

The safety data sheets, the labeling of the containers, the hazard warnings and the safety instructions on the containers must be observed during transport, storage and processing. The BG-Chemie data sheets must be observed during processing.

Do not allow to enter waters, drains or to penetrate the ground.

Disposal

Dispose of in accordance with the official regulations. Further information on disposal can be found in the respective safety data sheets, Section 13.

General information

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is therefore essential that you always have the latest data sheet to hand. The latest version can be downloaded from kemperol.de under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application tech-

nology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery

Issued: Vellmar, 2024-04-08