

KEMPEROL AC Speed



Uses

- As surface waterproofing, for creating connections and details in combination with KEMPEROL non-woven fabric
- As a waterproofing system under tarmac layers
- Suitable for outdoor applications
- For new buildings and repair work
- Can be applied to practically any substrate
- For OS10 systems

Characteristics

- Fast hardening
- Cold to process
- Water vapor diffusible
- Crack-bridging
- Root-resistant according to FLL test
- Accessible for maintenance purposes
- Solvent-free
- UV-resistant
- Environmentally declared according to valid international standards (EPD)
- 2-component
- Lightfast
- Processable down to -5 °C ambient temperature
- CE marking
- Red algae resistant
- Resin base: PMMA
- Alkali-resistant
- Radon-resistant

Pack sizes

15 kg container (component A) in conjunction with KEMPEROL CP catalyst powder (component B) Quantity added -see Table Hardening

Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

Usage guide

depending on the nature of the substrate: at least 2,5 kg/m² depending on the layer thickness (see Technical Information TI 03 - Layer thicknesses according to regulations).

Properties

Form	Comp. A liquid Comp. B powder
Standard colour	Traffic grey
Workability time*	approx. 20 min (2% KEMPEROL CP catalyst powder)
Rainproof after*	approx. 35 min
Can be walked on after*	approx. 35 min
Cured after*	approx. see the Hardening table**
Further coating after*	approx. 60 min ****
Short term temperature resistance	250 °C

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

** with KEMPERDUR Surfacing, see corresponding Technical Data Sheet.

CE marking

	ETA 12/0416
Water vapor diffusion resistance coefficient	$\mu \approx 6600$
Resistance to wind loads	1,6 N/mm ²
External fire performance	B _{ROOF(t1)} **
Reaction to fire	E ***
Statement to dangerous substances	does not contain any
Working life	W3
Climatic zones	M and S
Imposed loads	P1 to P4
Roof slope	S1 to S4
Lowest surface temperature	TL4

Highest surface temperature	TH4
-----------------------------	-----

** Classification in accordance with EN 13501-5
 *** Classification in accordance with EN 13501-1.

Curing

Hardening takes place with KEMPEROL CP catalyst powder. The quantity added depends on the temperature.

**Table for 15 kg
 KEMPEROL AC Speed waterproofing**

Temperature [°C]	KEMPEROL CP cat. powder - quantity [g]	Pot life in container [min]	Rainproof / surface cured [min]
-5°C	600	60 min	90 min
0°C	600	45 min	80 min
+5°C	600	35 min	70 min
+10°C	600	30 min	60 min
+20°C	300	20 min	35 min
+30°C	150	20 min	30 min

Application

Preparing the substrate

Substrates must be dry (residual moisture in concrete in the upper 2 cm < 5%), capable of withstanding loads and free from materials that may hinder adhesion, and must be appropriately prepared.

For some substrates, priming of the surface may not be necessary. Generally, the priming recommendations for KEMPEROL AC Speed waterproofing have to be observed.

When executed, the surface temperature must be 3 K above the dew point. If the dew point is undershot, a moisture film, which has a separating effect, can form on the surface to be processed (see Technical Information TI 16).

Preparation

If the ambient temperature is 10°C or lower, it is recommended that you store and mix the components at room temperature.

At temperatures above +25°C, protect the material against direct sunlight.

Mixing

KEMPEROL AC Speed waterproofing may only with KEMPEROL CP catalyst powder may be used. The quantity of the catalyst powder must be adapted to the respective material temperature (see Table Hardening KEMPEROL CP catalyst powder component B to be mixed thoroughly into KEMPEROL AC Speed waterproofing component A.

Use

The Waterproofing is produced by mixing KEMPEROL CP catalyst powder and KEMPEROL AC Speed waterproofing and KEMPEROL 165 fleece. Please refer to the instructions for use for further information.

Connections to door and window elements etc. with a height of <15 cm (from upper edge of coating) should have at least 5 cm of overlap. Connections and joints to third party products have to be produced with an overlap of at least 10 cm.

Avoid applying the material beyond the area covered by the fleece.

Work interruption and further coating

If the surface of the sealant is tack-free, it can be applied after approx. 60 minutes KEMPERDUR AC coating, KEMPERDUR AC Park, KEMPERDUR AC Park+ or KEMPERDUR AC-Finish .

During the further processing of KEMPERDUR MT mineral tile adhesive a bonding bridge is required.

PMMA surfaces must be cleaned with KEMCO MEK Cleaning Agent if left open for more than 3 days.

Note

Please consider the following technical information:

- TI 21 - substrate preparation
- TI 22 - Application of KEMPEROL/KEMPERDUR AC products
- TI 33 - Processing of / AC Speed+ Sealing at temperatures below +5°C
- TI 34 - Correct masking of the surface to be treated with KEMPEROL

Important notes

When applying KEMPEROL AC Speed waterproofing explosion protection for working equipment is necessary.

The applicable "rules of application" in its current version as well as the "standard rules of technology" and the state of the art for the respective task apply during waterproofing production. For chemical resistance, see the Chemical Resistance List A-Z.

The safety data sheets, the labeling of the containers, the hazard warnings and the safety instructions on the containers must be observed during transport, storage and processing. The BG-Chemie data sheets must be observed during processing.

Multi-component polyurethane, polyester, epoxy and methyl methacrylate resins react under heat development. After mixing the components, the product must not remain in the mixing container for longer than the

workability time. Non observance may cause heat and smoke development and may, in extreme cases, even result in a fire.

Disposal

Dispose of in accordance with the official regulations. Further information on disposal can be found in the respective safety data sheets, Section 13.

GISCODE

RMA10

General information

Changes to the colour caused by weather conditions or UV rays do not influence the technical parameters. The times given above are reduced with higher and increased with lower ambient and substrate temperatures.

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and our technical application advice only reflect the current state of knowledge in our company and our experience with our products. With each new edition, the previous technical information loses its validity. It is therefore essential that you always have the latest data sheet to hand. The latest version can be downloaded from kemperol.de under Media > Downloads. When applying and using our products, a detailed, object-related, qualified check is required in each individual case to determine whether the respective product and/or the application technology meets the specific requirements and purposes. We are only liable for the freedom from defects of our products, but only if our respective product has been used and processed in accordance with our processing guidelines in the technical data sheets. The proper and professional processing of our products is therefore the sole responsibility and liability of the user (processor). Our products are sold exclusively on the basis of our terms and conditions of sale and delivery.

Issued: Vellmar, 2024-03-12